

Release Agent MK-7070

Description:

Release Agent MK-7070 is a water-based "ready-to-use" - release agent, forming a coherent release film on the mould. Though this film is micro-thin, it is very resistant after cure, even to abrasive materials and temperature-stable up to 300°C. The product contains a slip agent, resulting in remarkably smooth surfaces, drastically reducing the friction between the elastomer and the release agent. Nevertheless, the strong chemical bonding to most mould materials, providing multiple releases per application, is not impaired. Release Agent MK-7070 does not transfer to the moulded parts, allowing further processing like varnishing or gluing without subsequent treatment. Build-up on the moulds caused by depositions of pigments, anti-aging agents, resin residues etc. is unlikely, if it is used as directed.

Application Fields:

Release Agent MK-7070 is suited as a release agent for the processing of all rubber types except silicone-rubber.

Application:

The first step is to thoroughly clean the mould. We recommend cleaning the molds with a fast evaporating solvent to be sure to have eliminated all grease- or wax- residues. As a priming coat 2 thin uniform layers of the release agent are applied to the hot mould. Longer drying time and higher temperature will result in improved durability and an increased number of possible releases per application. After this pre-treatment the processing can be started. To refresh the release film, it is sufficient to reapply one single, thin coat of Release Agent MK-7070 and let it dry sufficiently.

Technical Data:

Composition:	aqueous emulsion of synthetic resins
Appearance:	colourless fluid
Density [g/cm³]:	approx. 1
pH-value (20°C):	> 8

Packaging:

Can	30 kg
Drum	200 kg

Storage:

Release Agent MK-7070 should be stored in tightly sealed containers and has to be protected from frost, heat and direct sunlight. If these rules are obeyed, the product can be stored for at least 6 months. The expiry date is stated beneath the production date on the labels of each container.

Information for regulations on safety and transportation are provided in the safety data sheet

Product technical information and data is based on the best information available and does not constitute or imply a warranty or patent infringement of any kind. The user is responsible for testing product suitability prior to use in production.

Further information:

Page: 1 of 1
 Revision: 26.06.2009 HW/ts
 Print: 26.05.2010